PP HT9025ZK

总览/Overview

特点/Description	• 高流动 / High flow	• 高透明 / High Transparent	
应用/Application	• 高透明注塑制品/Highly transparent Injection Molding		
认证 / Certifications	• 食品卫生/Food hygiene	• FDA	• RoHS
加工方式/ Processing method	• 注塑 / Injection molding		

特性 Properties	单位 Units	典型值 Typical Value
熔体流动速率 Melt flow rate	g/10min	25
拉伸屈服强度 Tensile yield strength	MPa	23
弯曲模量 Flexural modulus	GPa	0.8
悬臂梁缺口冲击强度 Notched Izod impact Strength	23℃，KJ/m²	55

a. 以上数据为本色料的数据，染色料的性能数据可能与以上数据不一样。The above data is for the original color material, and the properties of the dyeing material may differ from theabove data.

b. 典型值是指实验室的平均数据，仅用于使用时参考，不作为产品标准。Typical values refer to the average data of the laboratory, which are only used as reference and are not used as product standards.

以上数值仅供参考使用，可根据制品大小、厚度以及产品要求做出调整 The above values are only for reference, and can be adjusted according to the size, thickness and requirements of the product.

Note:

1. 生产及操作时避免树脂接触到灰尘及杂物。 The resin should not contact with dust and sundries in processing.
2. 在射出周期中勿将热融胶长期停留在加热管中。 Do not Stay the resin in the heating tube for a long time during the injecting cycle.
3. 热浇道之系统温度不宜过高以免材料劣化。 The temperature of the hot runner should not be too high to avoid material degradation.
4. 加工的高温过程的水分控制是保证制品质量的关键之一。 The moisture control is one of the keys to ensure the quality of products in processing

以上数据为我公司测量之理论数据仅供参考，版权所有@东莞塑科化工有限公司
The above data is theoreticaldata measured by our company and is for reference only. All rights reserved @ Dongguan Suke Chemical Co., Ltd.